

Producer: LES BOROUGE PTE.LTD / UNITED ARAB EMIRATES (UAE)

HDPE HE3490LS

DESCRIPTION

BorSafe HE3490-LS is a black, bimodal, high density polyethylene classified as a MRS 10.0 material (PE100) produced by the advanced Borstar technology. Well dispersed carbon black gives outstanding UV resistance. Long term stability is ensured by an optimised stabilisation system.

APPLICATIONS

BorSafe HE3490-LS is recommended for pressure pipe systems in the applications field of drinking water and natural gas, pressure sewerage, relining, sea outfall and industrial. It is especially designed for the production of larger diameter, thick wall pipe, but can be processed for the whole range of diameters. It also shows excellent resistance to rapid crack propagation and slow crack growth.

PROPERTY	TEST	UNIT	VALUE
Density (Base resin)	ISO 1183/ISO 1872-2B	kg/m ³	949
Density (Compound)	ISO 1183/ISO 1872-2B	kg/m ³	959
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	<0.1
Melt Flow Rate (190°C/5.0 kg)	ISO 1133	g/10 min	0.25
Tensile Stress at Yield (50 mm/min)	ISO 527-2	Mpa	25
Tensile Strain at Break	ISO 527-2	%	>600
Tensile Modulus (1 mm/min)	ISO 527-2	MPa	1100
Charpy Impact, notched (0°C)	ISO 179/1eA	kJ/m ²	16
Hardness, Shore D	ISO 868	-	60
Carbon Black Dispersion	ISO 18553		<3
Carbon Black content	ASTM D 1603/ISO 6964	%	>2
Brittleness Temperature	ASTM D 746	°C	<-70
Resistance to Rapid Crack (Pc at 0°C, test pipe 250mm SDR11)	ISO 13477	bar	>10
Propagation, S4 test			
Resistance to Slow Crack (9.2bar, 80°C)	ISO 13479	h	>1000
Growth			
Thermal Stability (210°C)	EN 728	min	>20
ESCR (10% lgepal), F ₅₀	ASTM D 1693-A	h	>10000

PROCESSING GUIDELINES**Pre-drying**

Due to the hygroscopic nature of carbon black, this compound is sensitive to moisture. Storage for a long time or under unfavourable conditions will increase the moisture content. For normal conditions and applications we suggest preheating and drying for minimum 1 hour with a maximum preheat temperature of 90°C.

Extrusion

The actual extrusion conditions will depend on the type of equipment used. They will also depend on size and wall thickness of the pipe produced. The following conditions may be used as a guideline when starting up the extruder:

Cylinder	190 – 210°C
Head	200 – 210°C
Die	200 – 210°C
Melt temperature	200 – 220°C

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borouge representative for such particulars.

STORAGE AND HANDLING

BorSafe HE3490-LS should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

Improper storage can initiate degradation, which results in odour generation and can have negative effects on the physical properties of the product.

SAFETY

BorSafe HE3490-LS is not classified as dangerous preparation.

Dust and fines from the product carry a risk of dust explosion. All equipment should be properly earthed. Inhalation of dust should be avoided as it may cause irritation of the respiratory system. Small amounts of fumes are generated during processing of the product. Proper ventilation is therefore required.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

A Safety Information Sheet is available on request. Please contact your Borouge representative for more details on various aspects of safety, recovery and disposal of the product.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product:

Recovery and disposal of Polyolefins
Information on Emissions from Processing and Fires
Safety Information Sheet, SIS

Liability statements on:

- Compliance to Food Contact Regulations
- Compliance to Regulations for Drinking Water Pipes
- Statement on chemical, regulations and standards

DISCLAIMER

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borouge makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borouge products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.